

Butyl Tape: **OROTEX 381NS** has performed extremely well in the roofing, cabling, ducting, automotive and constructions industries, earning a well deserved reputation for being one of the best sealants.


Characteristic of Butyl tape: OROTEX 381NS

- **Waterproof**
- **Air Tightness**
- **Damping Properties**
- **Sound Insulating**
- **Stress Relaxation**
- **Self Adhesive**



Size : t2mmx100mmx10M/Rollx2Rolls/Box

Application is infinite. Shape freely !





Item		Specification	Result
Specific gravity		1.15 ~ 1.35	1.30
Penetration		60 ~ 80	63
Non-Volatile content (%)		98 min.	99
Tensile strength (kgf / cm ²)		0.3 min.	0.48
Elongation (%)		min. 1700	3,450
After aging	Tensile strength change (%)	40 max	19.6
	Elongation change (%)	50 max	3.8
Sagging Properties by Heat (°C)		50 min.	69
Shear Strength	Initial strength (kgf/25 x 6 mm)	0.9 min.	1.04
	After thermal aging (kgf/25 x 6 mm)	0.9 min.	1.49
Peel strength kgf/6mm	Initial strength	0.7 min.	0.9
	After thermal aging	0.7 min.	0.86
low-temperature adhesion (kgf/25 x 6 mm)		0.9 min.	1.19
Long Term adhesion kgf/25 x 6 mm		0.9 min.	1.74
Sealability mm		150 min.	Min. 504